




**LIFELAST**<sup>®</sup>  
*Innovation Through Formulation*



## DURASHIELD™ 310-61

### TECHNICAL DATA SHEET

EFFECTIVE: 6/24/2019

#### PRODUCT DESCRIPTION

##### CHEMICAL DESCRIPTION

Solventless Elastomeric Aromatic Polyurethane, Chemical Cure, ASTM D16 Type V

##### USAGE

DuraShield 310-61 (DS310-61) is a 100% solids, two-component polyurethane coating that contains no volatile organic compounds (VOC) or solvents. Formulated as a hard, durable, chemical resistant coating, DS310-61 also provides good flexibility and impact resistance for ferrous and non-ferrous metals, concrete and other surfaces. DS310-61 provides the low permeability and chemical resistance of an epoxy, with the durability, flexibility and fast cure times of polyurethanes. This blend of properties allows for excellent application characteristics, while at the same time making it ideal for long-term immersion protection. While DS310-61 has fast cure times, the nature of its chemistry allows for long recoat windows relative to comparative 100% solid urethanes. This helps to mitigate layering and recoat adhesion problems. DS310-61 is formulated to provide optimal build properties, often allowing for the required coating thickness to be applied in one coat – even on seams, welds and rivets – while at the same time providing good overcoat properties and aesthetics. Application of DuraShield 310-61 is primarily accomplished by spray (using an approved LifeLast spray system), however hand-applicable versions are also available.

##### COLORS

Standard color is almond. Gray and Black are also available.

##### QUALIFICATIONS

- Meets AWWA C222
- Certified to NSF/ANSI Standard 61 by the NSF for lining potable water tanks, pipes, valves, and fittings.
  - ◇ Pipe, Valves, Fittings ≥8"; thickness up to 250 mils
  - ◇ Tanks ≥50 gallons; thickness up to 250 mils
- FDA approved for dry bulk applications
- Meets USDA requirement for incidental contact
- USDA BioPreferred<sup>SM</sup>: Certified 64% Biobased Product

##### TYPICAL APPLICATIONS

- **Potable Water Pipe Linings**
- **Potable Water Tank Linings**
- **Lining for Potable Water Valves and Fittings**

#### PRODUCT ADVANTAGES

##### HIGHLY IMPERMEABLE

Provides excellent corrosion protection

##### GREAT CHEMICAL RESISTANCE

Withstands most concentrated acids and bases

##### ABRASION & IMPACT RESISTANT

Mitigates damage during handling and installation; protects against wear and erosion

##### EXCELLENT ADHESION

Bonds well to a wide array of substrates

##### GOOD FLEXIBILITY

Expands and contracts with the substrate; great impact resistance

##### HIGH BUILD CHARACTERISTICS

Application thicknesses from 20 mils to 250 mils in one application; completely encapsulates welds, rivets and edges

##### QUICK, INEXPENSIVE MAINTENANCE

Patch holidays and damage spots in minutes

##### LONG RECOAT WINDOW

Up to 24-hour recoat window is beneficial for multi-day applications, holiday repair, and addressing low millage areas.

#### COATING SYSTEMS

##### PRIMERS

- **Steel:** Self-priming
- **Non-Ferrous Metals & Galvanized Steel:** Self-priming, Primall-125 or Primall-160
- **Concrete & Wood:** Self-priming, Primall-125 or Primall-160

##### TOPCOATS \*

- Approved aliphatic urethanes. Consult a LifeLast representative for more information.  
\* For non-NSF applications

# DURASHIELD 310-61

## TECHNICAL DATA SHEET

EFFECTIVE: 6/24/2019

### TECHNICAL DATA

**SOLIDS**

100% by volume

**MIX RATIO BY VOLUME**

3 : 1 [DS310-61 (Polyol) : Activator 9000 (ISO)]

**RECOMMENDED DRY FILM THICKNESS**

20 mils up to 250 mils; thickness varies with application. Consult a LifeLast technical representative for information.

**COVERAGE**

- Theoretical: 80.2 ft<sup>2</sup>/gal @ 20 mils
- Spray: ≈70-75 ft<sup>2</sup>/gal @ 20 mils

**NET WEIGHT PER GALLON (ALMOND)**

- Polyol: 10.9 ± 0.2 lbs/gallon
- ISO: 10.3 ± 0.2 lbs/gallon
- Mixed: 10.7 ± 0.2 lbs/gallon

PHYSICAL PROPERTIES		
Test	Standard	Result
Adhesion to Steel	ASTM D4541; A.4	> 1500 psi
Tensile Strength	ASTM D412	2776 psi
Elongation at Break	ASTM D412	41%
Flexibility, 75 mils	ASTM D522	No cracking or delamination – ¾" Mandrel
Cathodic Disbondment	ASTM G95, Method A	<12 mm
Water Vapor Permeability	ASTM E 96 Procedure BW-Inverted Water Method	0.09 inch-pounds @ 53 mils
Water Absorption	ASTM D570	0.49%
Hardness, Shore D	ASTM D2240	70±3
Abrasion Resistance	ASTM D4060, CS17	45.1 mg
Impact Resistance	ASTM G14	120 in-lbs
Dielectric Strength	ASTM D149	527 V/mil
Service Temperature	Dry – Continuous: -40°F (-40°C) to 200°F (93°C) Maximum Surge: 350°F (177°C) Immersion – Insulated (max): 140°F (60°C) Non-Insulated: 120°F (49°C)	
Chemical Resistance	ASTM D543	Pass
Pickle Jar	(Greenbook) Section 211-2	Pass

**CURE TIME @ 70°F (21°C) - 75°F (24°C)\* @ 80 mils**

Designation	Standard	Fast Set
Tack Free	4 hours	50 min.
Recoat Time	24 hours	24 hours
To Immersion—NSF **	72 hours	72 hours
To Immersion—non-NSF	12 hours	2 hours
To Handling/Traffic	15 hours	4 hours

\* Varies by application technique, thickness & temperature

\*\* As per NSF Certification

**TIME TO HOLIDAY TEST**

Coating must be cured to handle before holiday testing.

**SHELF LIFE**

12 months at recommended storage temperatures in sealed, unopened containers.

**STORAGE**

- Temperature
  - ◊ Polyol: 40°F (4°C) - 120°F (49°C)
  - ◊ ISO: 40°F (4°C) - 120°F (49°C)
- Containers must be kept sealed in a dry environment.
- Contact LifeLast for continuous storage above 90°F (32°C).

**SHIPPING INSTRUCTIONS**

Unheated trailer, no special requirements. Keep dry.

### APPLICATION

**SURFACE PREPARATION**

Preparation requirements vary with application. Refer to the applicable *DuraShield 310 & DuraShield 310-61 Application Specification Sheet* or contact LifeLast for assistance.

**MIXING**

Power mix contents of polyol containers making sure to remove all pigment from the bottom of the container. Mixing of ISO is not required.

**POT LIFE**

12-15 minutes @ 75°F (24°C) (varies with batch size); ≈ 4 minutes @ spray temperatures for Standard speed

**SPRAY TEMPERATURE\***

Polyol: 120°F (49°C) - 150°F (66°C); ISO: 80°F (27°C) - 150°F (66°C)

\*Exact temperatures depend on spray equipment setup

**SURFACE TEMPERATURE**

Min. 40°F (4°C), Max 140°F (60°C); surface should be clean, dry and more than 5°F (-15°C) above dew point.

**AMBIENT CONDITIONS**

- Min. 0°F (-18°C), Max 120°F (49°C)
- Relative humidity should be less than 85%. Ambient air temperature must be no less than 5°F (-15°C) above the dew point.

**SPRAY EQUIPMENT**

Refer to the applicable *DuraShield 310 & DuraShield 310-61 Application Specification Sheet* for recommended spray equipment and setup. **Spray applicators and equipment must be certified by LifeLast.**

The information contained is offered without charge for technically qualified personnel at their discretion and risk. All statements, technical information and recommendations contained herein are based on tests and data believed to be reliable, but the accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto. We guarantee our products to conform to LifeLast quality control. Since conditions and methods of application are beyond our control, buyer assumes all risk of use or handling. LIFE LAST MAKES NO WARRANTY, EXPRESS OR IMPLIED, WITH RESPECT TO THE GOODS OR THE USE OF THE GOODS OR THE PERFORMANCE OF THE GOODS AND MAKES NO WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY UNLESS OTHERWISE STATED IN WRITING BY AN OFFICER OF LIFE LAST. Liability, if any, is limited to replacement of products. Data may be modified without prior notice.



*Innovation Through Formulation™*